



Quietspace® Panel is manufactured by Autex Australia Pty under an ISO 9001 and ISO 14001 certified Environmental and Quality Management System. The product is guaranteed to be free from manufacturing defects and carries a Manufacturer's Guarantee for a period of no less than ten years to meet all of the performance properties stated within this guarantee.

**Specification**

**Product Name** Quietspace® Panel  
**Description** 100% polyester needle punched, thermally bonded

	Metric			
Panel Dimensions	1200 mm x 2400 mm			
Tolerance	(±5 mm) (+10 mm)			
Thickness	25 mm	50 mm	75 mm	100 mm
Tolerance	(±/- 6%)			
Weight	2100 gsm	3600 gsm	3850 gsm	4100 gsm

**Physical Description /  
Properties**

Boiling Point:	N/A
Melting Point:	250°C
Vapour Pressure:	N/A
Specific Gravity:	Polyester 1.38
Flash point:	N/A
Explosive limits:	N/A
Solubility in water:	Not soluble
Alkalinity:	pH 7.8
Relative Vapour Density:	N/A

**Acoustic Performance**

Quietspace Panel is specifically designed to reduce and control reverberation and echo noise in building interiors.

Minimum Noise Reduction Coefficient 0.85

Frequency (Hz)	125	250	500	1000	2000	4000	NRC
● 25 mm	0.15	0.45	0.85	1.00	1.00	0.95	0.85
● 50 mm	0.30	0.75	1.10	1.10	1.05	1.00	1.00
● 75 mm	0.50	0.90	1.05	1.05	0.95	0.90	1.00
● 100 mm	0.65	1.00	1.05	1.00	0.95	0.90	1.00



## Service

For further information about Quietspace Panel or any other Autex product, please contact your Autex account manager or visit our website.

## Care and Maintenance

Maintain in accordance with the Care and Maintenance Guide available for this product.

## Product Specifications

### Composition

100% Polyester Fibre from polyethylene terephthalate (PET). Visage contains a minimum of 60% recycled polyester fibre.

### Suitable applications

Acoustic wallcovering. Accepts pins and staples.

### Light Reflectance

Nude White Quietspace Panel is suitable for indoor use only and has a light reflectance value of 83 (measured in accordance with BS 8493:2008+A1:2010).

### Fire Ratings

Quietspace® Panel has been evaluated using the following test methods:

#### ISO 9705: 1993

Classification: Group 1-S  
Smoke Production Rate: <5.0m<sup>2</sup>/s

As required by NZBC C/VM2

#### AS ISO 9705 - 2003

Classification: Group 1  
(SMOGR<sub>Arc</sub>): <100m<sup>2</sup>/s<sup>2</sup>

Assessed using methodology AS ISO 9705:2003 in accordance with AS 56371:2015, as required by BCA Specification C1.10-4  
FI 4871  
FAR 4055

### BS EN 13501-1:2018

(25 mm Quietspace® Panel)

Wall applications

Classification: B-s<sub>2</sub>,d<sub>2</sub>

Tested using BS EN ISO 11925-2:2020 and BS EN 13823:2020 and classified in accordance with BS EN 13501-1:2018, as required by BS EN 15102:2007 + A1:2011.

EUI-21-000135-E-A

Ceiling applications

Classification: B-s<sub>2</sub>,d<sub>2</sub>

Tested using BS EN ISO 11925-2:2020 and BS EN 13823:2020 and classified in accordance with BS EN 13501-1:2018, as required by BS EN 13964:2014.  
EUI-21-000135-E-B

### ASTM E84 - 14

(1" Quietspace® Panel)

Class A, FS:0 - SD:10

RJ3297

### Water Vapour Sorption

ASTM C1104 / C1104M-13a

Test conditions: 49°C, 95%RH  
Water vapour absorbed and adsorped after 4 days:  
0.4% by weight.

### Pattern Repeat

Non-woven. No pattern repeat but product has directional grain. Product may vary from samples and batch to batch due to fibre blending and lay-up, which is an inherent feature of this product.

### Impact Resistance

ISO 7892:1988

### Hard Body Impact

There is no surface damage or penetration to Quietspace Panel when subjected to hard body impacts. A small indentation might be observed when subjected to an impact equivalent to the impact of a 0.5 kg object dropped from a 0.5 m height.

When adhered to 10 mm plasterboard, the system can resist a 14 joule impact, and no further indentations are observed. This is equivalent to the impact of a 0.5 kg object dropped from a 3 m height.

### Soft Body Impact

There is no surface damage or penetration to Quietspace Panel when subjected to soft body impacts. When adhered to 10mm plasterboard, the system can resist a 120 joule impact. This is equivalent to the impact of a 50 kg object dropped from a 250 mm height.

### Microbial Resistance

ASTM G21-15

Growth Rating: 0 (No growth)

Quietspace Panel does not promote the growth of moulds and mildew.

### Colour Fastnes to light

Visage is suitable for indoor use only. Light fastness is dependent on use and exposure. Visage has been evaluated to the following standard:  
ISO 105-B02:2014  
Rating: 6 (Highest = 7)

### Colour Fastness to Rubbing

ISO 105-X12:2016

Dry Rating: 4-5 (Highest = 5)  
Wet Rating: 4-5 (Highest = 5)

### Fabric Care

Blot spills from fabric quickly. Wipe with a damp cloth. Avoid rubbing and excessive amounts of water as this will affect the finish.

Use carpet or upholstery shampoo as directed. Blot with a clean dry cloth after each application of solution

Custom printed Quietspace Panel requires the services of a specialist cleaning company. Refer to the Quietspace Panel Care and Maintenance Guide for more information.

● **New Zealand**  
702-718 Rosebank Road,  
Private Bag 19988  
Avondale 1746, Auckland  
T 0800 428 839  
T +64 9 828 9179  
[www.autexacoustics.co.nz](http://www.autexacoustics.co.nz)

● **Australia**  
285 Swan Street,  
Richmond, VIC 3121  
T 1800 678 160  
T +61 3 9450 6700  
[www.autexacoustics.com.au](http://www.autexacoustics.com.au)

● **United Kingdom**  
Unit J4, Lowfields Way,  
Lowfields Business Park,  
Elland, West Yorkshire  
HX5 9DA  
T +44 0 142 241 8899  
[www.autexacoustics.co.uk](http://www.autexacoustics.co.uk)

● **United States**  
1630 Dan Kipper Drive,  
Riverside, CA 92507  
T +1 424 203 1813  
[www.autexacoustics.com](http://www.autexacoustics.com)

Autex is an ISO certified organisation encompassing Quality (ISO 9001), Environmental (ISO 14001), and Health and Safety (ISO 45001). Brand names and logos are registered or unregistered trademarks owned or used under license by Autex Industries Limited or other members of the Autex Group. © Copyright 2023 Autex Industries Ltd. All rights reserved. It is the user's responsibility to determine if the product and information presented in this document is suitable for the intended application by engaging a suitably qualified consultant. The information contained in this document is correct to the best of our knowledge at the date of its publication. To verify that this document is the most current publication please check our website or contact your Autex account manager.